Japan Textile Products Quality and Technology Center

TEST REPORT

30th October 2020

APPLICATION

Test applicant : OHARA PARAGIUM CHEMICAL CO.,LTD
Test sample : Fabric (PARAFINE ANV-150GPF-7000 (After washing 10 times))
Test item : Antiviral Activity Test for Textile Product
Date of application : 8th September 2020

TEST METHOD

Antiviral activity of the test sample is tested mainly based on JIS L 1922 「Textiles -- Determination of antiviral activity of textile products」

○The Summary of Antiviral Activity Test for Textile Products

- Virus strain : Severe acute respiratory syndrome coronavirus 2 (SARS-CoV-2); JPN/TY/WK-521 (Distributed from National Institute of Infectious Diseases)
- Host cell : VeroE6/TMPRSS2 JCRB1819
- Growth medium : Dulbecco's modified Eagle's medium (low-glucose) ; DMEM (SIGMA, Cat#D6046)
  Minimum Essential Medium Eagle ; EMEM (SIGMA, Cat#M4655)
- Fetal Bovine Serum (FBS) (SIGMA, Cat#173012)

- Control specimen : Fabric (Blank)
- Antiviral test specimen : Fabric (PARAFINE ANV-150GPF-7000 (After washing 10 times))
- Wash-out solution : 1/10 SCDLP diluted with 2% FBS-containing DMEM
- Contacting time : 2 h at the temperature of 25 ºC
- Measurement of viral infectivity titer : Plaque assay

○Antiviral activity test

1.Preparation of test virus inoculum

1-1. Inoculate SARS-CoV-2 suspension on the surface of VeroE6/TMPRSS2 in the flask.
1-2. Put the flask in the CO_2 incubator to multiply SARS-CoV-2.
1-3. Centrifuge the multiplied virus suspension by using the centrifuge.
1-4. Take the supernatant suspension from the centrifugal tube after the centrifugation.
1-5. The virus suspension was proceeded with 10-fold dilution using distilled water as diluent.
1-6. The concentration of the virus suspension for the test after 10-fold dilution should be adjusted to a titer of 1×10^7 PFU/ml to 5×10^7 PFU/ml. This is to be the test virus suspension.

2. Inoculation of virus to the samples

Inoculate exactly 0,2 ml of the test virus inoculum to the several points of 0.4 g of specimen in the vial containers by pipette for all. Then put the caps on all vial containers and close them.

3. Contact
Put the vials in the incubator and keep for 2 h at the temperature of 25 ℃.

4. Wash-out of virus after contacting
After contacting for 2 h, add 20 ml of wash-out solution in the vial containers, then put the caps on the containers, close them and agitate them by Vortex mixer for 5 s and 5 times to wash out the virus from the specimens.

5. Virus infective titer measurement
Determine the virus infectivity titer by plaque assay.

○ Control test

1. Verification of cytotoxic effect

1-1. Put control specimens and antiviral test specimens in the vial containers.

1-2. Add 20 ml of wash-out solution in all containers. Then, put the caps on the containers and agitate them by Vortex mixer for 5 s and 5 times.

1-3. Observe if cells damage or not, by plaque assay.

2. Verification of cell sensitivity to virus and the inactivation of antiviral activity

2-1. Put control specimens and antiviral test specimens in the vial containers.

2.2. Add 20 ml of wash-out solution in all containers. Then, put the caps on the containers and agitate them by Vortex mixer for 5 s and 5 times.

2-3. Take 5 ml of washing out solution to new tubes.

2-4. Add 50 µl of virus suspension prepared to be a concentration of 5.0×10^4 PFU/ml into the tubes.

2-5. Keep them at 25 ℃ for 30 min.

2-6. Determine virus infective titer by plaque assay.

Japan Textile Products Quality and Technology Center

TEST RESULT

○Result of antiviral activity test

Virus strain : SARS-CoV-2; JPN/TY/WK-521
(Distributed from National Institute of Infectious Diseases)
Test virus suspension : 2.6×10^7 PFU/mL

Test Sample			Common logarithm value of Infectivity titer (PFU / vial) (Note 2)		Reduction value 【M】 (Note 4)	**Antiviral activity value (Mv)** (Note 3)
			Common logarithm	Common logarithm average		
Control specimen (Note 1)	Immediately after inoculation 【lg(V_a)】	n1	6.84	6.78	0.5	
		n2	6.79			
		n3	6.72			
	After contacting for 2h 【lg(V_b)】	n1	6.25	6.29		
		n2	6.29			
		n3	6.32			
Fabric (PARAFINE ANV-150GPF-7000 (After washing 10 times))	After contacting for 2h 【lg(V_c)】	n1	4.16	4.04	—	2.7
		n2	4.08			
		n3	3.87			

(Note 1) Fabric (Blank) is used for "control specimen".
(Note 2) PFU : plaque forming units (Note 3) Antiviral activity value (Mv)= $\lg(V_a) - \lg(V_c)$
(Note 4) Reduction value (M) = $\lg(V_a) - \lg(V_b)$ (Judgement of test effectiveness: $M \leq 1.0$)

○Result of control test
Virus strain : SARS-CoV-2; JPN/TY/WK-521
(Distributed from National Institute of Infectious Diseases)
Test virus suspension : 4.5×10^4 PFU/mL

Test Sample	Cytotoxic effect	Cell sensitivity to virus: Common logarithm average of Infectivity titer (PFU/mL) (Note 2)	Judgement of control test
Control specimen (Note 1)	negative	2.65	
Fabric (PARAFINE ANV-150GPF-7000 (After washing 10 times))	negative	2.66	satisfied

【Conditions for control test】
Cytotoxic effect : negative
Cell sensitivity to virus :
lg(Infectivity titer (PFU/mL) of control specimen) − lg(Infectivity titer (PFU/mL) of treated specimen) ≤0.5

Japan Textile Products Quality and Technology Center

<Reference date>

○Real-time RT-PCR measurement of virus suspension used in this test

- Virus strain : SARS-CoV-2; JPN/TY/WK-521
  (Distributed from National Institute of Infectious Diseases)
- Virus suspension : >10^8 PFU/ml
- Real-time PCR device : Thermal Cycler Dice® Real Time System Ⅲ (TaKaRa)
- Detection Kit : SARS-CoV-2 Detection Kit －N1 set－ (Code NCV-301; Lot# 038200)
  (TOYOBO CO.,LTD. Biotech support Department)

○Result

As the results of real-time RT-PCR measurement, an amplification of viral RNA in virus suspension used in this test was confirmed (Fig.1).



Fig.1. Real-time RT-PCR amplification plot

Red line shows the 10^{-2} dilution of virus suspension with PBS.
Blue line shows the 10^{-3} dilution of virus suspension with PBS.
Black line shows the 10^{-4} dilution of virus suspension with PBS.
Pink line shows the negative control; EMEM.

Yasuo Imoto
Microbial Testing Laboratory Kobe Testing Center
Japan Textile Products Quality and Technology Center